



PARACEM® QUARTZ

Dispersion paint with quartz effect

- Perfect saponification resistance
- durable
- fine quartz finish
- excellent weather resistance

PARACEM® QUARTZ

DESCRIPTION

Dispersion paint with quartz effect for outside and inside use.

RECOMMENDED USE

For protection of old deteriorated or cracked walls. Protection of concrete cell blocks against weather influences.

TECHNICAL DATA

Density (g/cm³):	± 1,65
Solids Content in weight:	73 - 75 %
Solids content in volume:	55 - 59 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to recoat:	8 hours
Fully cured:	1 day

RECOMMENDED WET FILM THICKNESS

300 µm

RECOMMENDED DRY FILM THICKNESS

175 µm

THEORETICAL CONSUMPTION

500 g/m² on even flat substrates. Minimum 1 kg/m² on structured substrates such as concrete cell blocks

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Cell concrete blocks: prime with Martin Mathys Pegafix or Primer 44HS

Walls in poor condition: remove all old coatings or bad plasterwork. Sand/treat the wall with a wire brush to remove all loose particles. Repair all damaged parts with a cement mortar or Martin Mathys Pegacrete. Small repairs can be treated with a mix of Paracem Quartz filled with dry sharp sand. All repairs should be primed with Martin Mathys Pegafix. Fill up holes and seal joints or fissures with Martin Mathys Elastofill.

New walls/masonry: if possible wait 1 year before treatment. The substrate must be sufficiently dry and stable and no bleeding of nitric acid should be visible.

Brush dry and dust, then apply a coat of Martin Mathys Pegafix or Primer 44 HS.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

> 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Apply with flat brush.

APPLICATION & THINNING: ROLLER

Apply with a mohair paint roller. When the applied paint film is still wet, roll a again with a slightly wet plastic foam roller for a good and equal finish.

APPLICATION & THINNING: AIRLESS SPRAY

Not advisable.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Possible with an opening diameter: 2 - 4 mm.

CLEANING OF EQUIPMENT / SPILLS

Water.

SAFETY DATA

VOC level:	30 g/l
VOC readymix:	30 g/l
VOC category:	A/c
VOC limit:	40 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 29/09/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu